




Technical Datasheet



Description	VALUE-PRO® 1K Primer, VP330-1120, is a 1K Aerosol Primer is designed and formulated for “Rub throughs” to bare metal and small spot repairs. It can be overcoated directly with topcoat systems.	
Products	VP330-1120 Value-Pro1K Primer	
Mixing	 Supplied Ready for use. Shake aerosol for at least 1 minute before use.	
Application	 Spraying Distance: 15 – 25cm	
Coats	 2 coats (thickness – approx 25 microns)	
Flash Time	 3 – 5 minutes between coats at 20°C	
Drying	 Air Dry at 20°C:	Recoatable: 10 -15 min.
Recoat	 Value-Pro 1K Rub Through Primer can be directly recoated with Value-Pro 2KBuild Primer.	
VOC Information The EU limit value for this product (product category: IIB.e) in ready to use form is max. 840g/litre of VOC. The VOC content of this product in ready to use form is max. 840g/litre. Depending on the chosen mode of use, the actual ready to use VOC of this product may be lower than that specified by the EU Directive code.		

These products are for professional painting only, and are not to be used for purposes other than those specified. The information on this TDS is based on present scientific and technical knowledge, and it is the responsibility of the user to take all necessary steps in order to ensure the suitability of the product for the intended purpose. For Health and Safety information please refer to the Material Safety Data Sheet.
September 2013

VALUE-PRO® & the VALUE-PRO® logo are trademarks of PPG Industries Ohio, Inc.© 2013 PPG Industries.
All rights reserved

PPG Industries (UK) Ltd
Auto Refinish
Customer Service & Sales Group,
Needham Road
Stowmarket, Suffolk.
IP14 2AD
Tel: 01449 771775